



ENDUTEX - REVESTIMENTOS TEXTTEIS, SA

VIZELA / PORTUGAL



TECHNICAL DATA SHEET

REFERENCE: OPAKJET

DESCRIPTION : PVC DOUBLE COATED HIGH TENACITY POLYESTER FABRIC

COMPOSITION : 82 % PVC
18 % POLYESTER

WIDTH : 137 - 150 - 160 - 220 - 320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.56	
TOTAL MASS (g/m ²)	710 ± 60	EN ISO 2286-2
FABRIC MASS (g/m ²)	130 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 250 T.: 140	EN ISO 1421
BREAKING EXTENSION (%)	L.: 18 T.: 18	EN ISO 1421
TEAR STRENGTH (daN)	L.: 20.0 T.: 14.0	DIN 53363
COATING ADHESION (daN/50mm)	min. 5.0	EN ISO 2411
COLOUR FASTNESS TO LIGHT	min 6	EN ISO 105-B02
LOW TEMPERATURE BEND TEST	No cracks at -25°C	EN 1876-1
FLAMMABILITY (mm/min)	< 100	DIN 75200

L - Along
T - Across

NOTE : Unless otherwise stated, the figures presented shall be regarded as typical values for the material, and not as a minimum to be satisfied.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2009.01.29	9		