



ENDUTEX - REVESTIMENTOS TEXTTEIS, SA

VIZELA / PORTUGAL



TECHNICAL DATA SHEET

REFERENCE: PRINT RC-3

DESCRIPTION : PVC DOUBLE COATED HIGH TENACITY POLYESTER SCRIM

COMPOSITION : 65 % PVC
35 % POLYESTER

WIDTH : 137 - 160 - 320 - 500 cm

CHARACTERISTIC	SPECIFICATION	METHOD
THICKNESS (mm)	0.60	
TOTAL MASS (g/m ²)	370 ± 30	EN ISO 2286-2
FABRIC MASS (g/m ²)	130 ± 10	EN ISO 2286-2
BREAKING LOAD (daN/50mm)	L.: 200 T.: 120	EN ISO 1421
BREAKING EXTENSION (%)	L.: 18 T.: 18	EN ISO 1421
TEAR STRENGTH (daN)	L.: 20 T.: 12	DIN 53363
COLOUR FASTNESS TO LIGHT	min 6	EN ISO 105-B02
AVERAGE PERMEABILITY OF FABRIC TO AIR (l/m ² /s)	3600	EN ISO 9237
AVERAGE LIGHT TRANSMISSION	24	SF 600 Plus Spectrophotometer
BURNING BEHAVIOUR	< 100	DIN 75200
OPEN AREA (%)	23	Internal

L – Along T - Across

NOTE : Unless otherwise stated, the figures presented shall be regarded as typical values for the material, and not as a minimum to be satisfied.

Date	Revision	QUALITY CONTROL	TECHNICAL MANAGER
2010.03.08	7		